



BSI Standards Publication

Leather - Chemical determination of metal content

Part 1: Extractable metals

National foreword

This British Standard is the UK implementation of EN ISO 17072-1:2019. It supersedes BS EN ISO 17072-1:2011, which is withdrawn.

The UK participation in its preparation was entrusted to Technical Committee TCI/69, Footwear & Leather.

A list of organizations represented on this committee can be obtained on request to its secretary.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

© The British Standards Institution 2019
Published by BSI Standards Limited 2019

ISBN 978 0 580 98548 5

ICS 59.140.30

Compliance with a British Standard cannot confer immunity from legal obligations.

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 30 April 2019.

Amendments/corrigenda issued since publication

Date	Text affected
------	---------------

Single User PDF Download Terms & Conditions

You have downloaded material which is subject to strict conditions of use. Copyright in this material is administered by Standards New Zealand on behalf of BSI. Please read these terms and conditions carefully, as in addition to the usual range of civil remedies available to Standards New Zealand for infringement of copyright, under New Zealand law every person who infringes copyright may be liable to a fine not exceeding \$50,000 or to imprisonment for a term not to exceed three months.

You have purchased a single-user licence to store this non-reviseable Adobe Acrobat PDF file on your personal computer. You may print out and retain ONE printed copy only.

BSI retains title and ownership of the copyright in this PDF file and the corresponding permitted printed copy at all times.

Under this licence use of both the PDF file and the single permitted printed copy of this PDF file you make are restricted to you. Under no circumstances are you permitted to sell, transfer or copy this PDF file, the one permitted printed copy of this PDF file, or any part of either of them.

You undertake that you will not modify, adapt, translate, reverse engineer, decompile, disassemble or create derivative works based on any of the downloaded PDF file, nor will you merge it with any other software or document, even for internal use within your organisation.

Under no circumstances may this PDF file be placed on a network of any sort without the express permission of Standards New Zealand, on behalf of BSI.

You are solely responsible for the selection of this PDF file and any advice or recommendation given by BSI or Standards New Zealand or its employees or agents about any aspect of this PDF file is intended for guidance only and is followed or acted upon entirely at your own risk.

Standards New Zealand is not aware of any inherent risk of viruses in this PDF file at the time that it is downloaded. Standards New Zealand has exercised due diligence to ensure, so far as practicable, that this file does not contain such viruses.

No warranty of any form is given by BSI or Standards New Zealand or by any party associated with BSI or Standards New Zealand with regard to this PDF file, and you accept and acknowledge that BSI and Standards New Zealand will not be liable in any way to you or any other person in respect of any loss or damage, however caused which may be suffered or incurred or which may arise directly or indirectly through any use of this PDF file.

Regardless of where you were when you downloaded this PDF file you accept and acknowledge that to the fullest extent possible you submit to New Zealand law with regard to this licence and to your use of this PDF file.

NOTES

31/10/2019, NZ Leather & Shoe Research Association purchased a single use licence to temporarily store this document on a single computer.
NZ Leather & Shoe Research Association may print and retain one copy only.

EUROPEAN STANDARD

EN ISO 17072-1

NORME EUROPÉENNE

EUROPÄISCHE NORM

April 2019

ICS 59.140.30

Supersedes EN ISO 17072-1:2011

English Version

Leather - Chemical determination of metal content - Part 1: Extractable metals (ISO 17072-1:2019)

Cuir - Détermination chimique de la teneur en métal
- Partie 1: Métaux extractibles (ISO 17072-1:2019)

Leder - Chemische Bestimmung des Metallgehaltes
- Teil 1: Extrahierbare Metalle (ISO 17072-1:2019)

This European Standard was approved by CEN on 9 February 2019.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Avenue Marnix 17, B-1000 Brussels

© 2019 CEN

All rights of exploitation in any form and by any means reserved
worldwide for CEN national Members

Ref. No. EN ISO 17072-1:2019: E

Version correct as of 31/10/2019

European foreword

This document (EN ISO 17072-1:2019) has been prepared by Technical Committee IULTCS "International Union of Leather Technologists and Chemists Societies" in collaboration with Technical Committee CEN/TC 289 "Leather" the secretariat of which is held by UNI.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by October 2019, and conflicting national standards shall be withdrawn at the latest by October 2019.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN ISO 17072-1:2011.

According to the CEN-CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

Endorsement notice

The text of ISO 17072-1:2019 has been approved by CEN as EN ISO 17072-1:2019 without any modification.

Contents

Page

Foreword	iv
1 Scope	1
2 Normative references	1
3 Terms and definitions	2
4 Principle	2
5 Reagents	2
5.1 General.....	2
6 Apparatus and materials	3
6.1 General.....	3
7 Sampling and sample preparation	3
8 Procedure	4
8.1 Preparation of acid artificial-perspiration solution.....	4
8.2 Extraction of leather sample.....	4
8.3 Analysis by ICP, AAS and SFA.....	4
8.3.1 General.....	4
8.3.2 ICP.....	5
8.3.3 AAS.....	5
8.3.4 Analysis by SFA technique.....	5
9 Calculation and expression of results	5
10 Test report	6
Annex A (informative) Interlaboratory test results and quantification limits	7
Bibliography	9

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see the following URL: www.iso.org/iso/foreword.html.

This document was prepared by the Chemical Test Commission of the International Union of Leather Technologists and Chemists Societies (IUC Commission, IULTCS) in collaboration with the European Committee for Standardization (CEN) Technical Committee CEN/TC 289, *Leather*, the secretariat of which is held by UNI, in accordance with the agreement on technical cooperation between ISO and CEN (Vienna Agreement).

IULTCS, originally formed in 1897, is a world-wide organization of professional leather societies to further the advancement of leather science and technology. IULTCS has three Commissions, which are responsible for establishing international methods for the sampling and testing of leather. ISO recognizes IULTCS as an international standardizing body for the preparation of test methods for leather.

This second edition cancels and replaces the first edition (ISO 17072-1:2011), which has been technically revised as follows:

- the Scope and [Clauses 5, 6, 7, 8.3, 9](#) and [10](#) have been editorially modified;
- [7.2](#) and [8.2](#) have been technically modified. 7.2 refers to ISO 4044 for sample preparation, which requires the user to grind sufficiently large pieces of leather or cut small pieces of leather;
- the previous subclauses 6.3 and 7.3 from ISO 17072-1:2011 have been deleted.

A list of all parts in the ISO 17072 series can be found on the ISO website.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

Leather - Chemical determination of metal content —

Part 1: Extractable metals

1 Scope

This document specifies a method for the determination of extractable metals in leather using extraction with an acid artificial-perspiration solution and subsequent determination with inductively coupled plasma optical emission spectrometry (ICP-OES), inductively coupled plasma mass spectrometry (ICP-MS), atomic absorption spectrometry (AAS) or spectrometry of atomic fluorescence (SFA).

This method determines extractable metals in leather; it is not compound-specific or specific to the oxidation state of the metals. This method is especially suitable for determining the extractable chromium in chromium-tanned leathers.

The method is applicable for the determination of many extractable metals, including:

Aluminium (Al)	Copper (Cu)	Nickel (Ni)
Antimony (Sb)	Iron (Fe)	Potassium (K)
Arsenic (As)	Lead (Pb)	Selenium (Se)
Barium (Ba)	Magnesium (Mg)	Tin (Sn)
Cadmium (Cd)	Manganese (Mn)	Titanium (Ti)
Calcium (Ca)	Mercury (Hg)	Zinc (Zn)
Chromium (Cr)	Molybdenum (Mo)	Zirconium (Zr)
Cobalt (Co)		

Interlaboratory test results and the quantification limits possible with ICP-OES are given in [Table A.1](#) and [Table A.2](#) of [Annex A](#).

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 105-E04, *Textiles — Tests for colour fastness — Part E04: Colour fastness to perspiration*

ISO 2418, *Leather — Chemical, physical and mechanical and fastness tests — Sampling location*

ISO 3696, *Water for analytical laboratory use — Specification and test methods*

ISO 4044, *Leather — Chemical tests — Preparation of chemical test samples*

ISO 4684, *Leather — Chemical tests — Determination of volatile matter*

ISO 11885, *Water quality — Determination of selected elements by inductively coupled plasma optical emission spectrometry (ICP-OES)*

ISO 15586, *Water quality — Determination of trace elements using atomic absorption spectrometry with graphite furnace*

ISO 17294-2, *Water quality — Application of inductively coupled plasma mass spectrometry (ICP-MS) — Part 2: Determination of selected elements including uranium isotopes*

ISO 17852, *Water quality — Determination of mercury — Method using atomic fluorescence spectrometry*

3 Terms and definitions

No terms and definitions are listed in this document.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <http://www.electropedia.org/>

4 Principle

A sample of leather is extracted at (37 ± 2) °C for $4 \text{ h} \pm 5 \text{ min}$ in an acid artificial-perspiration solution. The extract solution is filtered, acidified and analysed by ICP, SFA or AAS.

The results are reported on the dry matter of the leather.

5 Reagents

WARNING — The concentrated acids used in this method are very corrosive and/or oxidising liquids, which could raise the possibility of fire in the event of contact with ignitable materials and promote an existing fire considerably, or could decompose explosively with warming. They might cause acute or chronic health dangers as well. Moreover, they are hazardous to water. Suitable safety measures are therefore necessary.

5.1 General

Unless otherwise stated, only analytical grade chemicals shall be used. All solutions are aqueous solutions.

5.2 Nitric acid, 60 % to 70 % concentration (by mass).

5.3 L-histidine monohydrochloride monohydrate.

5.4 Sodium chloride.

5.5 Sodium dihydrogen phosphate dihydrate.

5.6 Sodium hydroxide, 0,1 mol/l.

5.7 Element stock solutions, of the various metals with mass concentrations of 1 000 mg/l each.

5.8 Nitric acid, 0,1 mol/l.

5.9 Water, grade 3 in accordance with ISO 3696.

5.10 Solution of gold (Au), in hydrochloric acid or potassium permanganate, 1 000 µg/l.

6 Apparatus and materials

6.1 General

All glassware, analytical devices and materials, including filters, shall be suitable for analysis of trace metals.

Use normal laboratory apparatus and, in particular, the following.

- 6.2 Laboratory oven**, capable of maintaining (102 ± 2) °C.
- 6.3 Analytical balance**, with an accuracy of 0,1 mg.
- 6.4 Laboratory balance**, with an accuracy of 0,01 g.
- 6.5 Membrane filters and holder**, suitable for filtering aqueous solutions, with a pore size of 0,45 µm.
- 6.6 Filtration device**, using glass fibre (GFC) or membrane type filters.
- 6.7 Volumetric flasks**, of various sizes (50 ml, 100 ml, 1 000 ml).
- 6.8 Erlenmeyer flasks**, of approximately 250 ml capacity, with stoppers.
- 6.9 Volumetric conical flasks**, of various sizes.
- 6.10 Water bath**, capable of maintaining (37 ± 2) °C, fitted with a horizontal flask shaker, frequency (60 ± 5) rpm, or orbital shaker, frequency (100 ± 10) rpm.
- 6.11 Inductively coupled plasma optical emission spectrometer (ICP-OES)** (see ISO 11885), with a hydride-generator module. The gases used shall be of analytical grade.
- 6.12 Flame or graphite-furnace atomic absorption spectrometer (AAS)** (see ISO 15586), with a hydride-generator module and suitable burner heads, and hollow-cathode-lamps. The gases used shall be of analytical grade.
- 6.13 Inductively coupled plasma mass spectrometer (ICP-MS)** (see ISO 17294-2). The gases used shall be of analytical grade.
- 6.14 Atomic fluorescence spectrometer (SFA)**, for mercury analysis.

7 Sampling and sample preparation

7.1 If the leather piece available for testing is a whole hide or skin, then the test specimens shall be sampled in accordance with the standard procedures given in ISO 2418. If sampling in accordance with ISO 2418 is not possible (e.g. leathers are from finished products like shoes or garments), details about the sampling shall be given in the test report.

7.2 Prepare the leather sample in accordance with ISO 4044. Test pieces that are wet (in excess of 30 % moisture) should be pre-dried for at least 12 h, at a temperature not exceeding (50 ± 2) °C. The drying temperature should be selected while considering the influence of elevated temperature on the nature of the analyte.

7.3 Determine the volatile matter content in accordance with ISO 4684. The same sample of leather can be used for the extraction in 8.2.

8 Procedure

8.1 Preparation of acid artificial-perspiration solution

Preparation of acid artificial-perspiration solution, shall be in accordance with ISO 105-E04. The solution shall be freshly prepared each day, containing, per litre:

- 0,5 g of L-histidine monohydrochloride monohydrate (5.3);
- 5 g of sodium chloride (5.4);
- 2,2 g of sodium dihydrogen phosphate dihydrate (5.5).

The solution is brought to pH ($5,5 \pm 0,1$) with 0,1 mol/l sodium hydroxide solution.

8.2 Extraction of leather sample

Weigh accurately 2 g of the prepared leather to the nearest 0,001 g using an analytical balance (5.3) and place in a 250 ml Erlenmeyer flask (5.8).

Add 100 ml of the acid artificial-perspiration solution (8.1) by pipette and, at (37 ± 2) °C, shake (6.10) in a water bath (6.10) for 4 h \pm 5 min.

In case of insufficient sample, it is possible to sample 1 g of leather, but in this case the extraction shall be performed with 50 ml of the acid artificial-perspiration in a 150 ml Erlenmeyer flask.

Filter the extract with a filter paper (6.6), then filter with a membrane filter (6.5).

In the case of Sn, Sb, Pb determination, check that the filtration doesn't cause a partial loss of these elements.

For the direct measurement of the elements, take a suitable amount of extract for analysis and add 5 % (by volume) of nitric acid (5.2). Consider this addition in the dilution factor.

To control the contaminants, it will be necessary to carry out a blank procedure. An aliquot of acid perspiration is placed in a sample container and treated as a sample, in all respects, including all analytical procedures.

The above extraction conditions shall be followed exactly. Any deviation would lead to the wrong results.

In the case of mercury (Hg) determination, add 10 μ l of gold solution (5.10) at the same time as the acid artificial-perspiration solution.

8.3 Analysis by ICP, AAS and SFA

8.3.1 General

The solution obtained in 8.2 can be analysed directly, provided it contains a concentration of analysed metals within calibration limits. Otherwise, the solution should be diluted as appropriate.

Prepare standard reference solutions of the required metals in accordance with ISO 11885, using perspiration solution (8.1), water or acidified water.

8.3.2 ICP

8.3.2.1 ICP-OES

Set up the ICP-OES (6.11) in accordance with the manufacturer's instructions and use the recommended settings indicated in ISO 11885.

Analyse the solution obtained in 8.2 against the reference solutions of metals with known concentration using ICP-OES (6.11) at the characteristic wavelength of each individual element.

8.3.2.2 ICP-MS

Set up the ICP-MS (6.13) in accordance with the manufacturer's instructions and use the recommended settings indicated in ISO 17294-2.

Analyse the solution obtained in 8.2 against the reference solutions of metals with known concentration using ICP-MS (6.13) at the characteristic ion mass of each individual element.

8.3.3 AAS

Prepare the atomic absorption spectrometer (6.12) following the manufacturer's instructions and use the recommended settings in accordance with ISO 15586.

Analyse the solution obtained in 8.2 against the reference solutions of metals with known concentration using AAS (6.12), with suitable hollow-cathode-lamp for each individual element.

8.3.4 Analysis by SFA technique

Set up the SFA (6.14) in accordance with the manufacturer's instructions and use the recommended settings indicated in ISO 17852.

Analyse the solution obtained in 8.2 against the reference solutions of mercury (Hg) with known concentration using SFA (6.14).

9 Calculation and expression of results

Express the result by stating the mass fraction (content) of the analysed metal, in milligrams per kilogram (mg/kg), calculated on the dry mass of the leather, as follows:

$$w_x = \frac{w_{x,i}}{m} \times V_1 \times F_d$$

where

- w_x is the mass fraction of the metal extracted from the leather, expressed in milligrams per kilogram (mg/kg) of analysed product, and rounded to the nearest first decimal place;
- $w_{x,i}$ is the concentration of the metal in question determined by the instrument, expressed in milligrams per litre (mg/l);
- m is the dry mass of the sample, expressed in grams (g), calculated in accordance with ISO 4684;
- V_1 is the volume of the acid artificial-perspiration solution for the extraction, expressed in millilitres (ml);
- F_d is the dilution factor eventually derived from the digestion procedure or acidification.

If required, the results can be given based on the dry, degreased mass of the leather sample. Details shall be noted in the test report.

10 Test report

The test report shall include at least the following information:

- a) name of the laboratory;
- b) a reference to this document, i.e. ISO 17072-1;
- c) a specification of the applied analytical system used;
- d) a description of the leather sample tested;
- e) results of the dry matter determination;
- f) results obtained for the amount of extracted metal, expressed in milligrams per kilogram of dry leather (mg/kg);
- g) details of any deviations from this standard test method.

Annex A (informative)

Interlaboratory test results and quantification limits

Table A.1 — Interlaboratory test for lead (Pb): statistical evaluation of results

Parameter	ISO 5725-2:1994 [1]	ISO 5725-5:1998 [2]
Number of participating laboratories	5	7
Overall mean value (mg/kg)	0,56	0,62
Repeatability standard deviation	0,029	0,050
Relative repeatability standard deviation	5,22	8,13
Standard deviation between laboratories	0,566	—
Reproducibility standard deviation	0,567	0,505
Relative reproducibility standard deviation	101,23	81,89
Repeatability factor	0,083	0,142
Reproducibility factor	1,604	1,429

Table A.2 — Quantification limit possible with ICP-OES

Metal Elements	Quantification limit (mg/kg)	
Aluminium	Al	100
Antimony	Sb	25
Arsenic	As	25
Barium	Ba	10
Cadmium	Cd	10
Calcium	Ca	100
Chromium	Cr	10
Cobalt	Co	10
Copper	Cu	10
Iron	Fe	25
Lead	Pb	25
Magnesium	Mg	100
Manganese	Mn	10
Mercury	Hg	0,02
Molybdenum	Mo	25
Nickel	Ni	10
Potassium	K	100
Selenium	Se	25
Tin	Sn	10
Titanium	Ti	10
Zinc	Zn	10

Metal Elements	Quantification limit (mg/kg)
Zirconium Zr	10

Bibliography

- [1] ISO 5725-2:1994, *Accuracy (trueness and precision) of measurement methods and results — Part 2: Basic method for the determination of repeatability and reproducibility of a standard measurement method*
- [2] ISO 5725-5:1998, *Accuracy (trueness and precision) of measurement methods and results — Part 5: Alternative methods for the determination of the precision of a standard measurement method*

British Standards Institution (BSI)

BSI is the national body responsible for preparing British Standards and other standards-related publications, information and services.

BSI is incorporated by Royal Charter. British Standards and other standardization products are published by BSI Standards Limited.

About us

We bring together business, industry, government, consumers, innovators and others to shape their combined experience and expertise into standards-based solutions.

The knowledge embodied in our standards has been carefully assembled in a dependable format and refined through our open consultation process. Organizations of all sizes and across all sectors choose standards to help them achieve their goals.

Information on standards

We can provide you with the knowledge that your organization needs to succeed. Find out more about British Standards by visiting our website at bsigroup.com/standards or contacting our Customer Services team or Knowledge Centre.

Buying standards

You can buy and download PDF versions of BSI publications, including British and adopted European and international standards, through our website at bsigroup.com/shop, where hard copies can also be purchased.

If you need international and foreign standards from other Standards Development Organizations, hard copies can be ordered from our Customer Services team.

Copyright in BSI publications

All the content in BSI publications, including British Standards, is the property of and copyrighted by BSI or some person or entity that owns copyright in the information used (such as the international standardization bodies) and has formally licensed such information to BSI for commercial publication and use.

Save for the provisions below, you may not transfer, share or disseminate any portion of the standard to any other person. You may not adapt, distribute, commercially exploit, or publicly display the standard or any portion thereof in any manner whatsoever without BSI's prior written consent.

Storing and using standards

Standards purchased in soft copy format:

- A British Standard purchased in soft copy format is licensed to a sole named user for personal or internal company use only.
- The standard may be stored on more than 1 device provided that it is accessible by the sole named user only and that only 1 copy is accessed at any one time.
- A single paper copy may be printed for personal or internal company use only.
- Standards purchased in hard copy format:
- A British Standard purchased in hard copy format is for personal or internal company use only.
- It may not be further reproduced – in any format – to create an additional copy. This includes scanning of the document.

If you need more than 1 copy of the document, or if you wish to share the document on an internal network, you can save money by choosing a subscription product (see 'Subscriptions').

Reproducing extracts

For permission to reproduce content from BSI publications contact the BSI Copyright & Licensing team.

Subscriptions

Our range of subscription services are designed to make using standards easier for you. For further information on our subscription products go to bsigroup.com/subscriptions.

With **British Standards Online (BSOL)** you'll have instant access to over 55,000 British and adopted European and international standards from your desktop. It's available 24/7 and is refreshed daily so you'll always be up to date.

You can keep in touch with standards developments and receive substantial discounts on the purchase price of standards, both in single copy and subscription format, by becoming a **BSI Subscribing Member**.

PLUS is an updating service exclusive to BSI Subscribing Members. You will automatically receive the latest hard copy of your standards when they're revised or replaced.

To find out more about becoming a BSI Subscribing Member and the benefits of membership, please visit bsigroup.com/shop.

With a **Multi-User Network Licence (MUNL)** you are able to host standards publications on your intranet. Licences can cover as few or as many users as you wish. With updates supplied as soon as they're available, you can be sure your documentation is current. For further information, email subscriptions@bsigroup.com.

Revisions

Our British Standards and other publications are updated by amendment or revision.

We continually improve the quality of our products and services to benefit your business. If you find an inaccuracy or ambiguity within a British Standard or other BSI publication please inform the Knowledge Centre.

Useful Contacts

Customer Services

Tel: +44 345 086 9001

Email (orders): orders@bsigroup.com

Email (enquiries): cservices@bsigroup.com

Subscriptions

Tel: +44 345 086 9001

Email: subscriptions@bsigroup.com

Knowledge Centre

Tel: +44 20 8996 7004

Email: knowledgecentre@bsigroup.com

Copyright & Licensing

Tel: +44 20 8996 7070

Email: copyright@bsigroup.com

BSI Group Headquarters

389 Chiswick High Road London W4 4AL UK